

Decorated MR E0 MDF - Gloss

Technical Data Sheet

Formica® Gloss Panels are manufactured on a durable Moisture Resistant (MR) Medium Density Fibreboard substrate providing a platform for a gloss decorative finish, suitable for vertical applications.

APPLICATIONS

Cabinetry

- Vanities
- · Cabinetry Doors & Drawers
- Wardrobes

Shelving

FUNCTIONAL BENEFITS



Vertical Application



Stain Resistant



Heat Resistant



Water Resistant



UV Stable Indoor Use

Product Characteristics

ATTRIBUTE	DESCRIPTION	
Product Category	Low Pressure Melamine	
Substrate Type	Moisture Resistant E0 MDF	
Sheet Size (nominal)	2400mm x 1200mm	
Thickness (nominal)	16mm	
Weight (Kg/m2 approx.)	12.9	
Finish	Gloss	
Colour/Pattern	To view the full range, please visit www.formica.com.au	

Technical Data Sheet

Dimensional Tolerance

(Tested to AS/NZS 4266.1)

ATTRIBUTE	MEASUREMENT	
Thickness	±0.6mm	
Length and Width	+5mm / -5mm maximum deviation	
Squareness	2mm/m maximum deviation	
Flatness	1.5mm/m maximum deviation (measured in horizontal)	

Surface Quality (Tested to AS/NZS 4266.2)

ATTRIBUTE	MEASUREMENT
Inspection Guidelines	Viewing distance 1.5m from decorative surface Light intensity approximately 800 to 1000 lx at the decorative surface Using normal vision, corrected if necessary. No magnification devices
Dirt, Spots & Similar Surface Defects	The admissible size of defects is based on a maximum contamination area equivalent to 1.0mm²/m² and is proportional to the sheet size under inspection
	The total admissible area of contamination may be concentrated in one spot or dispersed over an unlimited amount of smaller defects
Fibres, Hairs & Scratches	The admissible size of defects is based on a maximum contamination length equivalent to 10mm/m² and is proportional to the sheet size under inspection
	The total admissible length of contamination may be concentrated in one defect or dispersed over an unlimited amount of smaller defects

Technical Data Sheet

Surface Performance (Tested to AS/NZS 4266.2)

ATTRIBUTE	MEASUREMENT
Resistance to Surface Abrasion	Printed patterns ≥ 40 cycles. Solid colours ≥ 300 cycles
Resistance to Scratching	≥ 2 Newton
Porosity	Appearance rating not worse than 3
Resistance to Steam	Appearance rating not worse than 3 Moderate swelling
Resistance to Cracking	No visible cracks or micro cracks
Resistance to Staining	Rating ≤ 2 Faint stain left on surface
Lightfastness ISO 4586-2	Contrast: Grey scale rating ≥ 4 When tested in contrast with Blue wool 6 Ref: ISO 105-A02
Gloss Level at 60° angle AS/NZS 1580.602.2	≥ 105 gloss units (face side), ≥ 95 gloss units (back side)
Colour Variation ISO 105-A05	Surface material "batch to batch" colour variation of $\triangle E \le 1$

Adhesion Performance

(Tested to AS/NZS 4266.2)

Bond Strength ≥ 1.3 MPa

Technical Data Sheet

Substrate Performance (Tested to AS/NZS 4266.1)

MEASUREMENT

ATTRIBUTE	UNITS	MINIMUM VALUES	TYPICAL VALUES*	
- ·				
Density	Kg/m³		805 ± 20	
Internal bond	MPa	0.50	0.95 – 1.30	
Modulus of Rupture	MPa	26	44 - 47	
Modulus of Elasticity	MPa	2000	3300 - 3650	
Surface Soundness	MPa	0.9	1.4 - 1.7	
Screw Holding, Face	Force N	1500	1700 - 2000	
Screw Holding, Edge	Force N	900	1000 - 1300	
Thickness Swell (24hr)	%	(Max) 9.0	5.0 – 6.0	
Wet Bending Strength (Method A)	MPa	5	6 – 8	
Formaldehyde	mg/L	≤ 0.5	E0 ≤ 0.5	

[#] Table contains representative values only. Performance variation outside stated typical values does not constitute a product failure.

Specialty Performance

ATTRIBUTE	TESTED TO	TYPICAL VALUES	
	AS/NZS 3837 (In accordance to AS5637.1)	Group Number	3
Fire Hazard Properties		Average Specific Extinction Area (ASEA)	18.2 m²/Kg

Emissions & Environmental Performance

ATTRIBUTE	TESTED TO	UNITS	MEASUREMENT
Formaldehyde	AS/NZS 1859.2	mg/L	E0 ≤ 0.5
Volatile Organic Compounds (VOC's)	ASTM D5116	mg/m²/h	≤ 0.5

Technical Data Sheet

Important Information

NOTE		DETAILS		
$\overline{\mathbb{W}}$	ONLY use for internal applications	Claims arising from non-internal applications are not protected under warranty		
$\overline{\mathbf{w}}$	ONLY use for vertical applications	Claims arising from horizontal applications are not protected under warranty		
$\overline{\mathbf{w}}$	CAUTION! - Darker colours will show fingerprints, scratches and superficial wear & tear more readily than lighter colours	Claims arising from fingerprints, scratches or superficial wear & tear directly attributable to the selection of a dark colour, are not covered under warranty		
w	DO NOT expose to prolonged direct or indirect UV light	Claims arising from prolonged exposure to UV light (natural or artificial sources) resulting in shrinkage and/or colour changes beyond the tolerances stated in this document, are not protected under warranty		
w	Use of different surface materials within a single installation may result in a perceived visual variation	Claims arising from colour, gloss or finish variation between different product groups, including products with different UV or aging stabilities, are not covered under warranty		
w	ALL material must be inspected prior to commencing any fabrication activity	Claims arising from defects or variation clearly detectable prior to fabrication, will not be covered under warranty for labour costs or penalties		
$\overline{\mathbf{w}}$	ONLY the Functional Surface has the Gloss finish	Claims arising from gloss or texture variation between the Functional Surface and Complementary Coloured Backer are not covered under warranty		
$\overline{\mathbb{W}}$	ONLY use recommended hinge quantities	Claims arising from bow, warp or twisting due to too few hinges or inappropriate door sizes or weights, are not covered under warranty		
		Door Height (mm)	Door Weight (Kg)	No. of Hinges
		≤ 900 mm	≤ 9 Kg	2
		≤ 1600 mm	≤ 15 Kg	3
		≤ 2000 mm	≤ 19 Kg	4
		≤ 2400 mm	≤ 23 Kg	5
$\overline{\mathbf{w}}$	DO NOT use large door dimensions	Claims arising from bow, warp or twisting of doors greater than 600mm wide, are not covered under warranty		
		Claims arising from bow, warp or twisting of single piece doors greater than 1800mm high, are not covered under warranty. Pantry doors should use split door construction, where joinery brackets or connecting dowels can be used to join the two doors together		
w	DO NOT leave edges unsealed	Claims arising from the effect of heat or moisture ingress attributable to exposed edges of panels, are not covered under warranty		
$\overline{\mathbf{w}}$	DO NOT apply a coating to the surface	Claims arising from surface defects or other failure modes directly attributable to the application of paint or other surface lacquering systems, are not covered under warranty		

Technical Data Sheet

Important Information

NOTE		DETAILS	
w	DO NOT use for high impact or high abrasion installations	Claims arising from high impact or high abrasion installations are not protected under warranty	
$\overline{\mathbf{w}}$	DO NOT expose to heat, hot gases or moisture	Claims arising from frequent or excessive exposure to heat or moisture are not covered under warranty	
Ü	mosture	Claims arising from damage due to front venting oven installations without a heat deflector shield are not covered under warranty	
		Claims arising from damage due to fugitive heat or moisture leaking from appliance seals are not covered under warranty	
		Claims arising from the use of benchtop hot plates without exhaust fan activation or use of an ineffective extraction, are not covered under warranty	
w	ONLY use recommended Care & Maintenance methods	Claims arising from staining or damage attributable to not following Care & Maintenance instructions, are not covered under warranty	